

# MAX


## Photopolymer Plates

### MAXimum Print Quality Spanning a Broad Range of Package Printing

MacDermid MAX is the newest and best performing hard, analog sheet photopolymer plate from MacDermid. It is designed to deliver the MAXimum print benefit – low dot gain in screen/process color printing with smooth ink lay down for bold solids.

MAX plates work well with a wide variety of substrates and ink. This 60 durometer plate has excellent drape characteristics, making it well suited for applications involving small-diameter cylinders on narrow web presses. MAX is also an extremely low tack plate, which allows long, clean running print performance.

For eye-popping highlights, from the smallest to largest repeat lengths, count on the company that says “Yes We Can.” MacDermid.



### Key Features

- Excellent drape
- Low dot gain
- High resilience for clean running
- Extremely low tack (dry) plate
- Quick imaging

### Segments

Flexible Packaging



Folding Carton



Tags & Labels



Sacks, Paper, Multiwall



**YES WE CAN**<sup>SM</sup>

**MacDermid**  
Printing Solutions

# MAX

## Photopolymer Plates

### Technical Specifications

MAX is available in thicknesses of 0.030"(0.76 mm) - 0.112"(2.84mm) and in sizes up to 52" x 80"(1,320mm x 2,032mm). Please contact your MacDermid representative for details.

### Reproduction capabilities

**Halftones:** 0.030-0.112" gauge (0.76mm – 2.84mm)  
1-95% at 175 lpi (69 lines/cm)

**Fine lines:** 0.002 in. (0.05mm) width

**Isolated Dots:** 0.003 in. (0.08mm diameter)

Fine lines and isolated dots using 0.067 (1.70mm) plate

### Plate processing\*

Use with SOLVIT® QD is recommended. Most other safe-solvent solutions may be used.

Processing times for any particular job are determined by equipment, copy requirements and plate thickness.

### Recommended Processing Conditions\*

Gauge (mil/mm)	Durometer (Shore A)	Desired Relief (mil/mm)	Back exposure <sup>1</sup>		Face Exposure <sup>1</sup>		Wash out <sup>2</sup> (seconds)	Post exposure <sup>3</sup> (minutes)	Detack <sup>4</sup> (minutes)	Dry (min)
			(mJ/cm <sup>2</sup> )	(seconds)	(J/cm <sup>2</sup> )	(seconds)				
30 / 0.76	84	23 / 0.58	0	0	5.2-7.9	330-490	240	5	5	75
45 / 1.14	78	23 / 0.58	560	35	5.2-7.9	330-490	300	5	5	90
67 / 1.70	71	27 / 0.68	660	42	5.2-7.9	330-490	360	5	5	120
107 / 2.71	63	30 / 0.76	1,360	85	5.2-9.8	330-610	450	5	5	150
112 / 2.84	63	35 / 0.89	1,360	85	5.2-9.8	330-610	450	5	5	150

\*Contact your MacDermid representative for assistance in establishing proper processing conditions

1. Lamp intensity 16mW
2. Solvit QD washout times
3. Lamp intensity 17mW
4. Lamp Intensity 10mW

## YES WE CAN<sup>SM</sup>

It takes more than innovative, high performance products and superior technical service to help our customers compete and win in today's global marketplace. It takes a total commitment to understanding their needs and the ability to provide the right solutions—every time.

When success is your only goal, trust the company that says "Yes We Can."

### Ink/Solvent Compatibility

MAX plates have ink compatibility similar to natural rubber. Plates are compatible with water and alcohol based inks containing up to 25% acetate. MAX is not recommended for oil-based inks, hydrocarbon solvents, or inks with acetate ester content higher than 25%.

### Applications

MAX is an analog sheet photopolymer for use in labels, folding carton, multi-wall bag, preprinted liner, flexible packaging and other flexo markets that require a hard durometer plate.



For more information, please contact us at:

#### USA

5210 Phillip Lee Drive  
Atlanta, GA 30336  
Phone: 404.696.4565

#### Europe

3 rue de l'Industrie - BP 30160  
68702 Cernay Cedex, France  
Phone: +33 (0) 3 89 38 43 12

[www.macdermid.com/printing](http://www.macdermid.com/printing)